

HIGH STRENGTH RED THREADLOCKER - THREADLOCKER, RED HIGH STRENGTH,10ML BOTTLE

HIGH STRENGTH RED THREADLOCKER The Brownells High Strength Red Threadlocker is a premium adhesive designed for applications requiring a permanent bond on threaded fasteners. This high-strength threadlocker is ideal for securing bolts and screws that must remain fixed over time, effectively preventing loosening due to shock and vibration. It is particularly suitable for metal thread engagements where a robust hold is essential. Key Features: Permanent Bond: Provides a strong, enduring hold on threaded fasteners, ensuring components remain securely in place. Vibration Resistance: Effectively prevents loosening of metal thread engagements subjected to shock and vibration, maintaining assembly integrity. User-Friendly Application: Cures through the evaporation of water, simplifying the bonding process without the need for specialized equipment. Specifications: Container Sizes: Available in 1.8 ml and 10 ml tubes, accommodating both small-scale and more extensive applications. Color: Red, allowing for easy identification during application and inspection. Application Instructions: Surface Preparation: Ensure that parts are clean, dry, and free from oil or grease to promote optimal adhesion. Application: Apply the threadlocker to the threads, covering a length approximately 1.5 times the diameter of the part. Assembly: Assemble parts and tighten as required. Curing: Allow the product to cure through the evaporation of water to build strength. Instructions for Use: Parts must be clean, dry and free from oil or grease. Brownells High Strength Red Threadlocker cures through evaporation of water in order to build strength. It can be applied wet to threads and tightened or used to coat threads and allowed to dry before installation. Once set, disassembling parts with the threadlocker applied is achievable with the application of heat and standard tools. It is recommended to clean threads thoroughly with a brush and reapply the threadlocker when reassembling parts. Curing Time and Performance Temperature Range: Fixture Time: 15 - 20 minutes @ 72° F / 22° C Full Cure Time: 24 Hours @ 72° F / 22° C Temperature Range: -60° F to 300° F / -51° C to 150° C Safety Considerations: This product may cause skin and eye irritation. It is not recommended for use with plastics or in oxygen-rich environments. Please refer to the Safety Data Sheet (SDS) for detailed safety information. Incorporating the Brownells High Strength Red Threadlocker into your assembly process ensures that critical components remain securely fastened, enhancing the reliability and longevity of your equipment.



Attributes

- Name: THREADLOCKER, RED HIGH STRENGTH,10ML BOTTLE
- Manufacturer: BROWNELLS
- Product no.: 430110337
- Mfr. No.: 14010BROWN
- Color: Red
- Size: 10 mL
- Delivery weight: 0.045kg
- Shipping height: 92mm
- Shipping width: 29mm
- Shipping length: 29mm
- UPC: 050806001343

Item details

Made in USA

Table of Contents

- [Startpage](#)
- [Deutsch: Sicherheitsanweisungen für den Hochfesten Roten Gewindedichtstoff von Brownells](#)
- [English: Safety Instruction Guide for HIGH STRENGTH RED THREADLOCKER](#)

Sicherheitsanweisungen für den Hochfesten Roten Gewindedichtstoff von Brownells

Einleitung

Herzlichen Glückwunsch zu Ihrem Kauf des Hochfesten Roten Gewindedichtstoffs von Brownells. Dieser hochwertige Kleber wurde entwickelt, um eine dauerhafte Verbindung bei gewindetragenden Befestigungen zu gewährleisten. Um die Sicherheit bei der Verwendung des Produkts zu gewährleisten, befolgen Sie bitte die folgenden Anweisungen und Sicherheitsrichtlinien.

Allgemeine Sicherheitsrichtlinien

- **Produkt sicher verwenden:** Stellen Sie sicher, dass Sie alle Anweisungen befolgen, um eine sichere Anwendung zu gewährleisten.
- **Risikobewusstsein:** Seien Sie sich möglicher Risiken bewusst, die mit der Verwendung des Produkts verbunden sind, insbesondere Haut und Augenreizungen.
- **OnlineEinkauf:** Wenn Sie das Produkt online erwerben, stellen Sie sicher, dass der Verkäufer alle Sicherheitsanforderungen erfüllt.
- **Rückrufinformationen:** Überprüfen Sie regelmäßig die Rückrufupdates auf der Safety Gate Plattform der EU.
- **Sicherheitsdatenblatt:** Lesen Sie das Sicherheitsdatenblatt (SDS) für detaillierte Informationen zur Sicherheit und Handhabung des Produkts.

Spezifische Sicherheitsvorkehrungen für die Verwendung

- **Haut und Augenkontakt vermeiden:** Tragen Sie geeignete Schutzausrüstung, wie Handschuhe und Schutzbrille, um Haut und Augenreizungen zu vermeiden.
- **Luftzirkulation:** Verwenden Sie das Produkt in gut belüfteten Bereichen, um die Dämpfe zu vermeiden.
- **Nicht für Kunststoffe:** Verwenden Sie den Gewindedichtstoff nicht mit Kunststoffen oder in sauerstoffreichen Umgebungen.
- **Für Kinder unzugänglich aufbewahren:** Halten Sie das Produkt außerhalb der Reichweite von Kindern.

Anweisungen zur Installation und Verwendung

- **Oberflächenvorbereitung:**

- Stellen Sie sicher, dass die Teile sauber, trocken und frei von Öl oder Fett sind, um eine optimale Haftung zu fördern.

- **Anwendung:**

- Tragen Sie den Gewindedichtstoff auf die Gewinde auf, wobei eine Länge von etwa 1,5 Mal dem Durchmesser des Teils abgedeckt wird.

- **Montage:**

- Bauen Sie die Teile zusammen und ziehen Sie sie nach Bedarf an.

- **Aushärtung:**

- Lassen Sie das Produkt durch die Verdampfung von Wasser aushärten, um Festigkeit zu gewinnen.

- **Gebrauchsanweisung:**

- Die Teile müssen sauber, trocken und frei von Öl oder Fett sein.
- Der Gewindedichtstoff kann nass auf die Gewinde aufgetragen werden. Alternativ kann er verwendet werden, um die Gewinde zu beschichten und vor der Installation trocknen zu lassen.
- Nach dem Aushärten können Teile, auf die der Gewindedichtstoff aufgetragen wurde, mit Wärme und Standardwerkzeugen wieder auseinandergebaut werden.
- Es wird empfohlen, die Gewinde gründlich mit einer Bürste zu reinigen und den Gewindedichtstoff beim Wiederausbauen der Teile erneut aufzutragen.

- **Aushärtungszeit und Temperaturbereich:**

- Fixierzeit: 15 20 Minuten bei 72° F / 22° C
- Vollständige Aushärtungszeit: 24 Stunden bei 72° F / 22° C
- Temperaturbereich: 60° F bis 300° F / 51° C bis 150° C

Entsorgungsanweisungen

- Entsorgen Sie das Produkt gemäß den örtlichen Vorschriften für gefährliche Abfälle.
- Stellen Sie sicher, dass leere Behälter ordnungsgemäß entsorgt werden.

Kontaktinformationen für weitere Unterstützung

Für spezifische Fragen oder Unterstützung in Bezug auf die Verwendung des Produkts konsultieren Sie bitte die bereitgestellten Ressourcen oder wenden Sie sich an den Verkäufer.

Durch die Einhaltung dieser Sicherheitsanweisungen stellen Sie sicher, dass Sie den Hochfesten Roten Gewindedichtstoff von Brownells sicher und effektiv verwenden. Ihre Sicherheit und die Sicherheit anderer ist von größter Bedeutung.

Safety Instruction Guide for HIGH STRENGTH RED THREADLOCKER

Introduction

Thank you for choosing Brownells High Strength Red Threadlocker. This product is designed to provide a strong, permanent bond on threaded fasteners, ensuring that your components remain securely in place. To ensure safe and effective use, please follow the safety instructions and guidelines outlined in this document.

General Safety Guidelines

- Always read and understand the product label and safety instructions before use.
- Ensure the product is stored out of reach of children and pets.
- Use the product only for its intended purpose.
- Be aware of potential hazards associated with the product, including skin and eye irritation.
- In case of an emergency, seek medical attention immediately.

Specific Safety Precautions for Use

- **Skin Contact:** Avoid direct contact with skin. Wear gloves if necessary. If contact occurs, wash the area with soap and water.
- **Eye Contact:** Avoid contact with eyes. In case of contact, rinse immediately with plenty of water and seek medical attention.
- **Ventilation:** Use in a wellventilated area to minimize inhalation of vapors.
- **Compatibility:** Do not use with plastics or in oxygenrich environments as this may cause adverse reactions.
- **Heat Application:** Use standard tools and apply heat only as necessary for disassembly of parts.

Instructions for Installation and Usage

- **Surface Preparation:**
 - Ensure that parts are clean, dry, and free from oil or grease to promote optimal adhesion.
- **Application:**
 - Apply the threadlocker to the threads, covering a length approximately 1.5 times the diameter of the part.
- **Assembly:**
 - Assemble parts and tighten as required.
- **Curing:**
 - Allow the product to cure through the evaporation of water to build strength.
 - Fixture Time: 15 20 minutes at 72° F / 22° C.
 - Full Cure Time: 24 hours at 72° F / 22° C.
- **Disassembly:**
 - Once set, disassembling parts with the threadlocker applied is achievable with the application of heat and standard tools.
- **Reapplication:**
 - Clean threads thoroughly with a brush and reapply the threadlocker when reassembling parts.

Disposal Instructions

- Dispose of unused product and packaging according to local regulations.
- Do not dispose of the product in household waste.
- Contact local waste management authorities for proper disposal methods.

Contact Information for Further Support

For any safety inquiries or further assistance, please refer to the product packaging or contact your local distributor.

By following these safety instructions, you can ensure the safe and effective use of Brownells High Strength Red Threadlocker. Thank you for your attention to safety!

